

Informatii tehnice

FRONTLIT FLEX HEAVY CA-6 510GR

Item	Unit	Value		Test Method
Base Fabric	Denier	1000DX1000D		(High tenacity yarn) 100%PES
Construction	Weaving/inch	9x9		/
Weight of fabric	Gsm/m2	87±5		DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	423±5		DIN53352 BS3424 Method5B
Total weight	Gsm/m2	510±10		DIN53352 BS3424 Method5A
Thickness	mm	0.38±0.02		DIN EN ISO 2286-3
Width	cm	Up to 510		/
Tensile Strength	N/5cm	Warp	1500	DIN53352 BS3424
		Weft	1350	
Tearing Strength	N	Warp	260	DIN53356 BS3424
		Weft	205	
Adhesion	N/5CM	60		DIN53357 BS3425 Method9B
Temperature Resistance	℃	—20～70		DIN53357 BS3425 Method10
Lacquering	None			
Flammability	We can achieve: B1, B2, NFPA701, DIN75200 etc.			
LOW CADMIUM & HEAVY METALS	Can be applied for Cadmium free			
Conclusions and Announcements				